

Important information

The tables “Chemical resistance of plastics”, “Plastics and their properties” and “Viscosity of liquids” as well as the information about chemical resistance given in the particular product descriptions have been drawn up based on information provided by various raw material manufacturers. These values are based solely on laboratory tests with raw materials. Plastic components produced from these raw materials are frequently subject to influences that cannot be recognized in laboratory tests (temperature, pressure, material stress, effects of chemicals, construction features, etc.). For this reason the values given are only to be regarded as being guidelines. In critical cases it is essential that a test is carried out first. No legal claims can be derived from this information; nor do we accept any liability for it. A knowledge of the chemical and mechanical resistance alone is not sufficient for the evaluation of the usability of a product. For example, the regulations concerning flammable liquids (explosion prevention) must also be taken into consideration.

Copyright

This table has been published and updated by Bürkle GmbH, D-79415 Bad Bellingen as a work of reference. This Copyright clause must not be removed. The table may be freely passed on and copied, provided that the information about the publisher is retained.

Extensions, additions and translations

If your own experiences with materials and media could be used to extend this table then we would be pleased to receive any additional information. Please send an E-Mail to info@buerkle.de. We would also like to receive translations into other languages. Please visit our website at www.buerkle.de from time to time and download the updated version of these lists.

Publisher

Bürkle GmbH
Rheinauen 5
D-79415 Bad Bellingen
Tel +49 (76 35) 8 27 95-0
Fax +49 (76 35) 8 27 95-31
info@buerkle.de
www.buerkle.de

Version 3.9 (11.01.2021)

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics													fluoroplastics		elastomers		metals		Haste/ly C	COMMENT					
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM / FKM			NBR	SI	AL	V2A	V4A
Acetaldehyde	C ₂ H ₄ O	000075-07-0	40 %	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	3/4	Acetic aldehyde; Ethanal; Ethyl aldehyde
Acetaldehyde	C ₂ H ₄ O	000075-07-0	techn. pure	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Acetamide	C ₂ H ₅ NO	000060-35-5	saturated	Xn		1/1	1/1	1/0	4/4	0/0	1/1	1/0	1/1	1/1	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	1/0	0/0	(1)	(1)	(1)	1/1	
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	50 %	C		1/1	1/1	4/4	1/2	0/0	1/1	3/4	1/1	2/2	2/2	1/2	0/0	0/0	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/1	1/1	1/1	
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	100 %	C+	X	0/0	0/0	4/4	4/4	(3)	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1	
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	90 %	C+	X	1/1	1/2	4/4	4/4	4/4	1/3	4/4	1/2	4/4	3/4	1/2	4/4	4/4	1/1	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1	
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	10 %	Xi		1/1	1/1	4/4	1/2	1/1	3/0	1/4	1/1	1/1	1/0	1/3	1/0	1/3	1/1	1/1	1/1	1/1	(2)	(3)	3/3	0/0	1/3	1/1	1/1	1/1	
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	5 %	Xi		1/1	1/3	4/4	1/2	1/1	1/1	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/1	1/1	
Acetic acid chloride	-> see: Acetyl chloride																														
Acetic acid sodium salt	-> see: Sodium acetate																														
Acetic aldehyde	-> see: Acetaldehyde																														
Acetic anhydride	C ₄ H ₆ O ₃	000108-24-7	techn. pure	C	X	4/4	3/3	3/3	4/4	0/0	4/4	(2)	1/3	4/4	4/4	4/4	0/0	0/0	1/0	1/1	4/4	3/0	4/4	4/4	0/0	(2)	1/1	1/1	1/1		
Acetic chloride	-> see: Acetyl chloride																														
Acetone	C ₃ H ₆ O	000067-64-1		F, Xi	X	1/1	3/3	1/0	4/4	4/4	2/3	1/3	1/3	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	3/4	1/0	4/4	4/4	0/0	1/1	1/1	1/1	1/1	Propanone, 2-; Dimethyl ketone; Methyl ketone
Acetonitrile	C ₂ H ₃ N	000075-05-8		F, T	X	1/1	1/1	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	0/0	1/1	(1)	(1)	1/1	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	Methyl cyanide; Cyanomethane; Ethanenitrile
Acetonyl chloride	-> see: Chloroacetone																														
Acetophenone	C ₈ H ₈ O	000098-86-2		Xn		0/0	1/0	1/0	(4)	(4)	(4)	1/0	1/3	0/4	0/0	4/4	4/4	0/4	1/1	0/0	1/1	1/3	1/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0	Phenylethanone, 1-; Phenyl methyl ketone; Acetylbenzene
Acetyl chloride	C ₂ H ₃ ClO	000075-36-5	100 %	F, C	X	0/0	0/0	4/4	4/4	(4)	(4)	4/4	3/4	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/2L	1/1L	0/0	Acetic chloride; Ethanoyl chloride; Acetic acid chloride	
Acetylene	C ₂ H ₂	000074-86-2	100 %	F+	X	1/0	1/0	1/0	1/0	1/1	0/0	1/0	1/0	0/0	0/0	2/0	4/4	3/0	(1)	1/1	1/0	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	1/1	Ethine; Ethyne
Acetyloxybenzoic acid, 2-	-> see: Acetylsalicylic acid																														
Acetylsalicylic acid	C ₉ H ₈ O ₄	000050-78-2	100 %	Xn		0/0	0/0	1/0	0/0	(2)	0/0	(3)	1/2	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/2	(2)	(3)	0/0	0/0	1/0	1/0	1/0	1/0	Acetyloxybenzoic acid, 2-;
Acrylonitrile	C ₃ H _{3.5} N	000107-13-1		F, T	X	1/1	1/3	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	1/2	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/0	1/0	1/0	1/1	1/1	Cyanoethylene; Propenenitrile, 2-; Vinyl cyanide
Adipic acid	C ₆ H ₁₀ O ₄	000124-04-9	saturated	Xi		1/1	1/2	0/0	1/1	(2)	1/1	1/3	1/1	1/1	2/2	1/3	1/3	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	1/0	(2)	1/1	Hexanedioic acid; Butanedicarboxylic acid, 1,4-	
Alanine, L-	C ₃ H ₇ NO ₂	000056-41-7				1/1	1/1	1/1	4/4	(2)	1/1	(1)	1/1	1/1	4/4	4/4	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(2)	(2)	(2)	Aminopropanoic acid, L-2; aminopropanoic acid, alpha-	
Allspice	-																														
Allyl acetate	C ₆ H ₁₀ O ₂	000591-87-7	100 %	F, T	X	0/0	1/3	4/4	4/4	(4)	(4)	(2)	1/3	4/4	0/0	0/0	4/4	0/0	(1)	1/1	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)	(1)		
Allyl alcohol	C ₃ H ₆ O	000107-18-6	96 %	F, T	X	1/3	3/3	3/0	3/3	1/0	1/2	(2)	2/2	2/4	2/3	2/3	4/4	4/4	1/1	1/1	(2)	1/0	4/4	3/0	0/0	1/1	1/1	1/1	1/1	Vinyl carbinol; Propenyl alcohol	
Allyl chloride	C ₃ H ₅ Cl	000107-05-1	100 %	F, T+	X	(3)	3/4	0/0	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	1/1	4/4	(3)	4/4	0/0	1/0	(1L)	(1L)	0/0	Chloro-1-propene, 3-; Chloropropylene, 3-	
Allyl mustard oil	C ₈ H ₁₂ NS	000057-06-7		T	X	0/0	0/0	0/0	(4)	(3)	(4)	(2)	0/0	0/0	0/0	4/4	0/0	0/0	(1)	(1)	(2)	(3)	4/4	0/0	(1)	(1)	(1)	(1)	(1)	oleum sinapis	
Almond oil, sweet	-																														
Alumina acidic	C ₂ H ₇ AlO ₅ x H ₂ O	000142-03-0	saturated	Xi		1/1	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(1)	1/1	1/1			
Aluminium fluoride	AlF ₃	007789-18-1	aqueous	Xi		1/1	1/1	(3)	(2)	(2)	1/1	3/4	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	0/0	0/0	
Aluminum ammonium sulfate dodecahydrate	(NH ₄) ₂ Al(SO ₄) ₂	007784-26-1	saturated	Xi		1/1	1/1	3/4	(2)	0/0	3/4	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	1/1	0/0	1/0	1/2	1/3	0/0			
Aluminum chloride	AlCl ₃	007784-13-6	10 %	?		1/1	1/2	1/0	1/0	(2)	1/1	3/4	1/1	0/1	0/1	0/1	0/1	1/1	2/2	1/1	1/1	1/1	1/0	1/0	1/1	0/0	4/4	4/4	3/4	1/1	
Aluminum chloride	AlCl ₃	007784-13-6	solid	C		1/1	1/1	3/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	(3)	(3)	0/0	4/4	4/4	3/4	1/1			
Aluminum chloride	AlCl ₃	007784-13-6	saturated	C		1/1	1/1	3/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	1/1	(1)	1/1	(2)	1/0	1/1	0/0	4/4	4/4	3/4	1/1			
Aluminum hydroxide	Al(OH) ₃	021645-51-2		Xi		1/1	1/2	1/1	1/1	1/1	1/2	1/1	1/2	2/2	2/2	1/2	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	small solubility - no chemical effect expected
Aluminum nitrate	Al(NO ₃) ₃	013473-90-0	aqueous	(O)		1/1	1/0	1/4	1/0	(2)	1/0	3/4	1/1	1/0	1/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1	
Aluminum oxide, alpha-	Al ₂ O ₃	001344-28-1	solid			1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	small solubility - no chemical effect expected
Aluminum potassium sulfate	KAl(SO ₄) ₂ x 12H ₂ O	010043-67-1	diluted	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Aluminum potassium sulfate	KAl(SO ₄) ₂ x 12H ₂ O	010043-67-1	saturated	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	(1)	(1)	0/0	
Aluminum sodium sulfate	NaAl(SO ₄) ₂	010102-71-3		?		1/1	1/1	(3)	(2)	(1)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(2)	0/0	1/3	(1)	(1)		
Aluminum sulfate	Al ₂ (SO ₄) ₃	010043-01-3	10 %	?		1/1	1/1	1/0	1/0	(2)	1/1	3/4	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/2	1/1	
Aluminum sulfate	Al ₂ (SO ₄) ₃	010043-01-3	saturated	Xn		1/1	1/1	3/4	1/0	0/0	1/1	3/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	2/2	1/2	1/1	
Aminic acid	-> see: Formic acid																														
Aminoacetic acid	-> see: Glycine																														
Aminoethanol	C ₂ H ₇ NO	000141-43-5		Xn/Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/2	4/4	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0		
Aminopropanoic acid, alpha	-> see: Alanine, L-																														
Ammonium acetate	Nickel-chromium-m	000631-61-8	saturated	Xi		1/1	1/1	1/0	1/1	(2)	1/1	(1)	1/1	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(3)	2/2	0/0	1/1	(2)	(2)	1/1	
Ammonium bicarbonate	CH ₃ NO ₃	001066-33-7	saturated	Xi</																											

CHEMICALS	thermoplastics															fluoroplastics			elastomers			metals			COMMENT									
	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM / FKM		NBR	SI	AL	V2A	V4A	Hastelloy C			
Ammonium chloride	(NH ₄)Cl	012125-02-9	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/1	2/3	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1	sal ammoniac				
Ammonium difluoride	F ₂ H ₂ N	001341-49-7	50 %	T, C		1/1	1/1	2/0	(4)	0/0	0/0	(4)	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/0	(3)	2/3	0/0	(3)	1/0	1/0						
Ammonium ferric sulfate	(NH ₄)Fe(SO ₄) ₂	007783-83-7	saturated	Xi		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	(1)	0/0	(4)	0/0	0/0							
Ammonium ferrous sulfate	(NH ₄) ₂ Fe(SO ₄) ₂	007783-85-9		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	(1)	(1)						
Ammonium fluoride	(NH ₄)F	012125-01-8	saturated	T, C		1/1	1/1	1/0	4/4	(2)	1/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	(1)	(1)	?					
Ammonium fluoride	(NH ₄)F	012125-01-8	aqueous	T, C		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	1/3	1/3	1/1					
Ammonium glycolate	C ₂ H ₇ NO ₃	035249-89-9		(Xi)		1/1	1/2	(1)	2/3	(2)	1/2	(2)	1/2	1/1	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	(2)	(2)	(2)		Acetic acid			
Ammonium heptamolybdate	(NH ₄) ₆ Mo ₇ O ₂₄	012054-85-2		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	(1)	1/0	(3)	(1)	0/0		(1)	(1)	0/0					
Ammonium hydroxide	NH ₃ + H ₂ O	001336-21-6	30 %	C, N		1/1	1/2	(3)	4/4	2/4	1/2	1/2	1/2	2/3	2/3	1/2	0/0	0/0	1/1	1/1	(2)	1/0	(3)	2/3	0/0	1/1	1/1	1/1	1/1					
Ammonium hydroxide	NH ₃ + H ₂ O	001336-21-6	5 %	Xi		1/1	1/1	(2)	3/4	(2)	1/1	1/2	1/1	1/3	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(2)	2/3	0/0	1/1	1/1	1/1	1/1				
Ammonium hydroxide	NH ₃ + H ₂ O	001336-21-6		C/Xi, N		1/1	1/1	(3)	4/4	2/4	1/1	1/2	1/1	2/3	2/3	1/2	1/3	2/2	1/1	1/1	1/1	1/3	1/0	(3)	4/4	0/0	1/1	1/1	1/1	1/1				
Ammonium mercaptan	-> see: Ammonium bisulfide																																	
Ammonium nitrate	(NH ₄)NO ₃	006484-52-2	10 %	O		1/3	0/0	1/0	(1)	(2)	0/0	2/4	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	1/1	1/1	1/1	1/1	Nitric acid; Ammonium salt			
Ammonium nitrate	(NH ₄)NO ₃	006484-52-2	saturated	O		1/3	1/1	1/0	1/0	(2)	1/1	2/4	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	(2)	1/1	1/1	1/1				
Ammonium nitrite	(NH ₄)NO ₂	013446-48-5	aqueous	O, Xn		(1)	(1)	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/0	0/0	(2)	(1)	(1)						
Ammonium oxalate	C ₂ H ₄ N ₂ O ₄	014258-49-2		Xn		1/1	1/2	(1)	1/1	(2)	1/2	(2)	1/2	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	1/1	1/1	1/1	0/0				
Ammonium persulfate	(NH ₄) ₂ S ₂ O ₈	007727-54-0	saturated	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0					
Ammonium persulfate	(NH ₄) ₂ S ₂ O ₈	007727-54-0	aqueous	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0					
Ammonium phosphate, Mono-	(NH ₄)H ₂ PO ₄	007722-76-1	each	Xi		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	3/0	1/1	0/0	4/4	(1)	(1)	1/1					
Ammonium polyphosphate (APP)	(NH ₄ PO ₃) _n	068333-79-9		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	1/1	0/0	(3)	(1)	(1)					
Ammonium rhodanide	-> see: Ammonium thiocyanate																																	
Ammonium salt	-> see: Ammonium nitrate																																	
Ammonium sulfate	(NH ₄) ₂ SO ₄	007783-20-2	10 %	Xn		1/1	1/1	1/0	1/1	(2)	(1)	1/0	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/1	1/1				
Ammonium sulfate	(NH ₄) ₂ SO ₄	007783-20-2	saturated	Xn		1/1	1/1	1/0	1/1	(2)	1/1	2/0	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/2	1/1				
Ammonium sulfide	(NH ₄) ₂ S	012135-76-1	each	T, C	X	1/1	1/1	1/0	4/4	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/2	0/0	1/1	(1)	(1)	?	Diammonium sulfide;			
Ammonium sulfide	(NH ₄) ₂ S	012135-76-1	aqueous	T, C	X	1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	(1)	(1)	1/1					
Ammonium sulfo cyanide	-> see: Ammonium thiocyanate																																	
Ammonium thiocyanate	CH ₄ N ₂ S	001762-95-4		Xn		1/1	1/1	(3)	1/0	(2)	1/1	1/0	1/1	1/3	0/0	1/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(3)	1/0	0/0	(2)	(1)	(1)		Ammonium sulfo cyanide; Ammonium rhodanide; Thiocyanic acid, Ammonium salt, Ammonium sulfo cyanate			
Amomum	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)					
Amyl acetate, normal	C ₇ H ₁₁ O ₂	000628-63-7		—	X	1/2	2/3	2/0	4/4	1/3	2/3	(1)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	3/4	4/4	0/0	1/1	1/1	1/1	1/1	0/0				
Amyl alcohol, n-	-> see: Pentanol, 1-																																	
Amyl chloride	C ₅ H ₁₁ Cl	000543-59-9		F, Xn	X	3/4	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	3/4	3/4L	3/4L	0/0				
Amyl cinnamic aldehyde	C ₁₄ H ₁₈ O	000122-40-7		Xi		0/0	0/0	0/0	(4)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(4)	(3)	(4)	0/0	(1)	(1)		odoriferous substance			
Aniline	C ₆ H ₇ N	000062-53-3		T		1/2	1/3	3/4	4/4	0/0	2/3	1/3	2/3	4/4	4/4	4/4	4/4	0/4	2/4	1/1	1/1	1/4	4/4	2/4	4/4	0/0	1/0	1/0	1/0	1/1				
Aniline hydrochloride	C ₆ H ₇ ClN	000142-04-1	saturated	T		1/3	0/0	(3)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	3/0	2/2	3/3	0/0	4/4	4/4	4/4						
Anise	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)						
Anise oil	—	084775-42-8		Xi		0/0	0/0	(3)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(1)	(1)	(1)	0/0				
Anisole	C ₇ H ₈ O	000100-66-3	100 %	Xi	X	1/4	3/4	1/0	4/4	0/0	2/3	(2)	3/3	4/4	0/0	0/0	0/0	1/1	1/1	(3)	4/4	4/4	0/0	1/0	(1)	(1)	(1)	0/0						
Antifreeze agent (car)	—	—		Xn		1/1	1/1	3/3	(1)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	1/0	1/2	1/1	0/0	(1)	1/1	1/1		glycol-water-mixture				
Antimony pentachloride	SbCl ₅	007647-18-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	(2)	4/4	0/0	(3)	(4)	(4)	0/0					
Antimony trichloride	SbCl ₃	010025-91-9	90 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4	0/0					
Antimony trichloride	SbCl ₃	010025-91-9	anhydrous	C		0/0	0/0	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	1/0	1/0	1/0	0/0	1/1	4/4	4/4						
Antimony trichloride	SbCl ₃	010025-91-9	aqueous	C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4						
Apple juice	—	—		—		1/1	1/1	(1)	1/0	1/0	0/0	(2)	1/1	0/0	0/0	0/0	1/1	1/1	1/															

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics													fluoroplastics		elastomers		metals		Hastelloy C	COMMENT											
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM / FKM			NBR	SI	AL	V2A	V4A						
Butyl alcohol, sec-	C ₄ H ₁₀ O	000078-92-2		Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	1/1	2/3	2/2	2/3	2/2	2/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)	Butanol, -2; Methyl ethyl carbinol; Butylene hydrate
Butyl alcohol, tert-	C ₄ H ₁₀ O	000075-65-0		F, Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	1/1	2/3	2/2	2/3	2/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)						
Butyl aldehyde	-> see: Butyraldehyde																																				
Butyl carbinol, n-	-> see: Pentanol, 1-																																				
Butyl ether, (Di-) n-	C ₈ H ₁₈ O	000142-96-1	techn. pure	Xi	X	3/4	1/4	(2)	(3)	1/0	(4)	(1)	3/4	0/0	3/0	4/4	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	4/4	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	Butoxybutane, 1-;			
Butyl ethylene	-> see: Hexene, 1-																																				
Butyl stearate	C ₂₂ H ₄₄ O ₂	000123-95-5	100 %	Xi		0/0	0/0	(1)	(3)	1/0	0/0	(2)	(2)	0/0	0/0	1/0	1/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1	0/0					
Butylamine	C ₄ H ₁₁ N	000109-73-9		F, C	X	0/0	0/0	0/0	(3)	0/0	0/0	3/4	2/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0						
Butylene glycol	C ₂ H ₁₀ O ₂	—	techn. pure	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	4/4	(1)	0/0	1/1	(1)	(1)	0/0		isomer not indicated in the source			
Butylene hydrate	-> see: Butyl alcohol, sec-																																				
Butylphenol	C ₁₀ H ₁₄ O	—	100 %	Xi		0/0	1/1	(3)	(3)	0/0	(3)	(4)	1/1	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	isomer not indicated in the source		
Butylphenol, p-tert	C ₁₁ H ₁₆ NO	000098-54-4	techn. pure	C, Xn		3/0	0/0	(3)	(3)	0/0	(3)	(4)	1/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1				
Butyraldehyde	C ₄ H ₈ O	000123-72-8		F, Xn	X	0/0	0/0	(3)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)					Butanal; Butyl aldehyde			
Butyric acid	C ₄ H ₈ O ₂	000107-92-6		C		3/4	4/4	3/3	4/4	0/0	4/4	4/4	4/4	4/4	2/2	2/4	4/4	4/4	1/1	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/2	1/2	1/1	1/1						
Cadmium bromide	CdBr	007789-42-6		T		1/1	1/1	(3)	(2)	0/0	(3)	(1)	1/1	0/0	0/0	0/0	1/1	0/0	1/1	0/0	1/1	1/1	1/1	(1)	(2)	(2)	4/4	0/0	4/4	0/0	0/0						
Calcium bicarbonate	Ca(HCO ₃) ₂	—	saturated	—		1/1	1/1	1/1	(1)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	(1)	0/0	(2)	(1)	(1)	0/0							
Calcium bisulfite	Ca(HSO ₃) ₂	013780-03-5	saturated	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	1/1							
Calcium bisulfite	Ca(HSO ₃) ₂	013780-03-5	aqueous	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	1/1							
Calcium bromide	CaBr ₂	007789-41-5	?	?		1/1	1/1	(2)	(1)	2/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(3)	0/0	0/0	0/0								
Calcium carbide	CaC ₂	000075-20-7		F	X	1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	0/0	(3)	(1)	(1)	0/0					carbide, reacts with water to acetylene - highly flammable!				
Calcium carbonate	CaCO ₃	000471-34-1	saturated	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0		small solubility - no chemical effect expected			
Calcium chlorate	Ca(ClO ₃) ₂	010137-74-3	saturated	O, (T)		0/0	0/0	(3)	(2)	0/0	1/1	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(2)	(1)	(3)	0/0	1/1	(1)	1/0	1/1								
Calcium chloride	CaCl ₂	010043-52-4	alkoholic	F, Xi		1/0	0/0	4/4	(2)	0/0	1/0	(3)	1/1	0/0	0/0	0/0	4/4	0/0	0/0	1/1	1/0	(1)	(2)	(2)	0/0	(3)	1/2L	1/2L	1/1								
Calcium chloride	CaCl ₂	010043-52-4	aqueous	Xi		1/1	1/1	1/0	1/0	1/1	(3)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/3	1/2L	1/2L	1/1							
Calcium hydroxyde	CaH ₂ O ₂	001305-62-0	aqueous	(Xi)		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	0/0							
Calcium hydroxyde	CaH ₂ O ₂	001305-62-0	concentrated	C		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	2/2	2/2	1/1	1/0	0/0	1/1	1/1	1/1	1/3	1/0	1/1	1/0	0/0	3/4	1/1	1/1	0/0							
Calcium hypochlorite	Ca(OCl) ₂	007778-54-3	saturated	O, C		1/1	1/1	1/4	3/4	3/0	1/2	1/0	1/1	2/3	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/3	(2)	2/3	4/4	0/0	4/4	3/0	2/0	1/1			bleaching powder				
Calcium hypochlorite	Ca(OCl) ₂	007778-54-3	aqueous	O, C/Xi		0/0	0/0	4/4	1/0	3/0	0/0	1/0	1/1	1/3	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	4/4	0/0	4/4	3/0	2/0	1/1			bleaching powder					
Calcium nitrate	Ca(NO ₃) ₂	010124-37-5	50 %	O		1/1	1/1	(2)	1/0	(2)	1/1	(3)	1/1	0/0	0/0	0/0	1/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	4/4	0/0	1/0	1/1	1/1	1/1							
Calcium nitrate	Ca(NO ₃) ₂	010124-37-5	aqueous	O		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/0	1/0	1/0	1/1	1/1	1/1							
Calcium oxide	CaO	001305-78-8	powder	C		1/0	1/1	(2)	(2)	(2)	0/0	0/0	1/1	1/1	0/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	1/1	1/1									
Calcium phosphate	Ca ₃ (PO ₄) ₂	007758-87-4	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0		small solubility - no chemical effect expected				
Calcium phosphate	Ca ₃ (PO ₄) ₂	007758-87-4	—	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0		small solubility - no chemical effect expected				
Calcium sulfate	CaSO ₄	007778-18-9	saturated	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0		plaster					
Calcium sulfide	CaS	020548-54-3	aqueous	C		0/0	0/0	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/0	(1)	(1)	0/0								
Calcium sulfide	CaS	020548-54-3	—	C		0/0	3/3	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/0	(1)	(1)	0/0								
Calciumacetat	C ₄ H ₈ CaO ₄	000062-54-4	aqueous	—		1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(2)	(1)	(1)	0/0								
Camphor	C ₁₀ H ₁₆ O	000464-48-2 / -49-2		F, Xn	X	3/4	3/4	(2)	(3)	0/0	0/0	(2)	1/0	1/3	0/0	4/4	4/4	1/1	0/0	(1)	1/0	(3)	4/4	3/4	1/0	0/0	(1)	1/0	1/0	1/0							
Camphor oil	—	008008-51-3		Xn		4/4	4/4	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	(3)	4/4	3/0	1/0	0/0	(1)	(1)	(1)	1/0		from cinnamomum camphora					
Caprylic alcohol	C ₈ H ₁₆ O	000111-87-5		Xi		0/0	0/0	(2)	(2)	(1)	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)								
Caraway	—	—	ground	?		0/0	0/0	(2)	(2)	(1)	0/0	1/1	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	4/4	(1)	(1)								
Carbazole	C ₁₂ H ₉ N	000086-74-8		Xn		1/1	1/1	(2)	4/4	0/0	1/1	(1)	1/1	1/1	4/4	4/4	0/0	4/4	1/1	1/1	(2)	(2)	(3)	(2)	0/0	(1)	(1)	(1)	0/0								
Carbolinum	—	008001-58-9	aqueous	(Xn)		1/0	1/0	1/0	(3)	1/0	0/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(2)	3/0	1														

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics													fluoroplastics		elastomers		metals		Hastelloy C	COMMENT																											
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM			NBR	SI	AL	V2A	V4A																						
Diocetyl sebacate	C ₂₆ H ₅₀ O ₄	002432-87-3				0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)		plasticiser																							
Dioxane	C ₈ H ₁₆ O ₂	000123-91-1		F, Xn	X	2/2	2/3	1/0	4/4	1/0	2/3	1/2	3/3	4/4	2/3	3/4	4/4	4/4	1/3	1/1	1/1	3/3	2/0	4/4	4/4	0/0	1/1	1/0	1/0	0/0																							
Diphenyl ether	C ₁₂ H ₁₀ O	000101-84-8		Xn/Xi		0/0	1/0	3/0	(3)	(4)	0/0	1/1	4/4	4/4	0/0	4/4	4/4	0/0	(1)	1/0	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)	(1)	0/0																							
Diphenylamine	C ₁₂ H ₁₁ N	000122-39-4		T		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)	0/0																							
Diphyl	—	008004-13-5		?		0/0	0/0	1/1	(3)	4/4	0/0	1/1	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)		mixture with diphenyl and diphenyl ether; Bayer																						
Dipropyl ketone	C ₇ H ₁₄ O	000123-19-3			X	0/0	0/0	(3)	(4)	(4)	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)	(1)																								
Dipropylene glycol	C ₈ H ₁₄ O ₃	025265-71-8		Xi		1/1	1/1	(2)	2/3	0/0	1/1	1/0	1/1	1/1	2/2	2/3	0/0	0/0	1/1	1/1	(1)	(2)	4/4	3/0	3/3	0/0	(1)	(1)	(1)																								
Dipropylene glycol (mono)methyl ether	C ₈ H ₁₆ O ₂	—			X	0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	isomer not indicated in the source																						
Disodium phosphate	Na ₂ HPO ₄	007558-79-4		(Xi)		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	(1)	1/1	1/1	0/0																								
Dispersion of rubber	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(1)	(2)	0/0	(3)	(1)	(1)		latex																						
Dithionous acid, disodium salt	-> see: Sodium hydrosulfite																																																				
Divinylene oxide	-> see: Furan																																																				
Dope, viscous -	—	—		(Xn, Xi)		1/1	1/1	4/4	(3)	0/0	0/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	(3)	(2)	4/4	0/0	(3)	3/4	2/4	0/0																								
Emulsifiers	—	—		?		0/0	0/0	(2)	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(3)	0/0	0/0	K	K																								
Emulsions for fotos	—	—		?		1/0	0/0	1/0	(2)	(2)	0/0	1/0	1/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(1)	0/0	(2)	0/0	0/0	0/0																								
Ephetin	—	—	10% in water	?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0																								
Epichlorhydrin	C ₃ H ₇ ClO	000106-89-8	100 %	F, T	X	1/0	1/0	4/4	(4)	0/0	(4)	1/0	2/2	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(3)	3/0	4/4	4/4	0/0	(3)	0/0	0/0	0/0																							
Epoxypropane, 1,2-	-> see: Propylene oxid																																																				
Ethanal	-> see: Acetaldehyde																																																				
Ethanedioic acid	-> see: Oxalic acid																																																				
Ethanenitrile	-> see: Acetonitrile																																																				
Ethanoyl chloride	-> see: Acetyl chloride																																																				
Ethoxybenzene	C ₈ H ₁₀ O	000103-73-1		?		0/0	0/0	(2)	(4)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		Ethyl phenyl ether; Phenyl ethyl ether; Phenetole																							
Ethyl acetate	C ₄ H ₈ O ₂	000141-78-6	100 %	F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/1	1/3	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	3/3	3/0	4/4	4/4	0/0	1/1	(1)	(1)	1/0																							
Ethyl acrylate	C ₈ H ₁₀ O ₂	000140-88-5	100 %	F, Xn	X	4/4	4/4	1/0	(4)	(4)	(4)	(2)	4/4	0/0	4/4	4/4	0/0	0/0	1/1	1/0	3/0	4/4	4/4	4/4	0/0	(1)	(1)	(1)	1/0																								
Ethyl alcohol	C ₂ H ₆ O	000064-17-5	40 %	—	X	1/1	1/2	1/0	1/2	1/1	1/2	1/1	2/3	1/2	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1																							
Ethyl alcohol	C ₂ H ₆ O	000064-17-5	50 %	—	X	1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	1/1																							
Ethyl alcohol	C ₂ H ₆ O	000064-17-5	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	1/1																							
Ethyl aldehyde	-> see: Acetaldehyde																																																				
Ethyl benzoate	C ₈ H ₁₀ O ₂	000093-89-0		Xn		2/2	3/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)																								
Ethyl butyrate	C ₈ H ₁₂ O ₂	000105-54-4		F	X	2/3	2/4	(2)	4/4	0/0	3/4	(2)	2/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)																								
Ethyl chloride	-> see: Monochloroethane																																																				
Ethyl chloroacetate	C ₄ H ₇ ClO ₂	000105-39-5	techn. pure	T/Xi		1/1	1/1	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/4	3/4	0/0	0/0	(1)	1/1	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0																							
Ethyl cyanoacetate	C ₃ H ₅ NO ₂	000105-56-6		Xn/Xi		1/1	1/1	0/0	3/4	0/0	1/1	(2)	1/1	2/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(3)	4/0	0/0	(2)	(1)	(1)	0/0																							
Ethyl formate	C ₃ H ₆ O ₂	000109-94-4		F	X	0/0	0/0	0/0	(4)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)																									
Ethyl lactate	C ₅ H ₁₀ O ₃	000097-64-3		—	X	1/1	1/1	(2)	3/4	0/0	1/1	(2)	1/1	3/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	3/0	(3)	(3)	(3)	0/0	(1)	(1)	(1)																								
Ethyl mercaptan	C ₂ H ₆ S	000075-08-1		F, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)																									
Ethyl phenyl ether	-> see: Ethoxybenzene																																																				
Ethyl silicate	C ₈ H ₂₀ SiO ₄	000078-10-4		Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	1/0	0/0	(1)	(1)	(1)																									
Ethylbenzene	C ₈ H ₁₀	000100-41-4		F, Xn	X	2/3	3/4	(2)	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	1/1	4/4	(2)	4/4	0/0	(1)	(1)	(1)	0/0																								
Ethylene	C ₂ H ₄	000074-85-1		F+	X	0/0	0/0	1/0	(2)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(2)	(3)	3/0	3/3	0/0	(1)	(1)	(1)	0/0																								
Ethylene dibromiden (EDB)	C ₂ H ₄ Br ₂	000106-93-4		T		(4)	(4)	(2)	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/2	4/4	(3)	4/4	0/0	(3)	1/0L	1/0L	0/0		Dibromoethane, 1,2-;																						
Ethylene glycol	C ₂ H ₆ O ₂	000107-21-1		Xn		1/1	1/1	3/3	2/3	1/0	1/1	(2)	1/1	2/4	3/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/2	1/0	0/0	1/1	1/1	1/1	1/1																							
Ethylene glycol monobutyl ether	C ₈ H ₁₆ O ₂	000111-76-2	100 %	Xn	X	0/0	1/0	1/0	(2)	1/0	0/0	1/0	1/0	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	1/1	3/0	3/4	3/4	0/0	1/1	(1)	(1)	0/0																							
Ethylene glycol monoethyl ether	C ₄ H ₁₀ O ₂	000110-80-5	100 %	T	X	0/0	4/4	(3)	(2)	0/0	0/0	1/0	2/4	4/4	1/0	4/4	4/4	4/4	0/0	1/1	1/0	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0																							
Ethylene glycol monoethyl ether acetate	C ₆ H ₁₂ O ₃ </																																																				

CHEMICALS	thermoplastics										fluoroplastics			elastomers			metals			Hastelloy C	COMMENT										
	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE			FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A
Exhaust gases, containing hydrochloric acid	—	—	each	?	1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	2/2L	2/2L	3/3		
Exhaust gases, containing hydrogen fluoride	—	—	small	?	1/1	0/0	(3)	(3)	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	(2)	(2)	1/1		
Exhaust gases, containing nitrose	—	—	small	?	1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/3	0/0	0/0	(2)	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	(3)	0/0	(2)	(1)	(1)			
Exhaust gases, containing sulfur dioxide	—	—	small	?	1/1	0/0	(2)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	1/1	1/1	0/0		
Exhaust gases, containing sulfur trioxide	—	—	small	?	1/1	0/0	(4)	0/0	0/0	0/0	(4)	4/4	0/0	0/0	1/1	0/0	0/0	(2)	(2)	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	0/0		
Exhaust gases, containing sulfuric acid	—	—	each	?	1/1	0/0	(4)	0/0	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	0/0		
Fat, animal	—	—	—	—	0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Fat, mineral	—	—	—	(—)	0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	(1)	1/0	0/0	(1)	1/1	1/1			
Fat, vegetable	—	—	—	—	0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1			
Fats, edible oil	—	—	—	—	0/0	1/0	1/0	1/0	1/0	1/0	1/1	3/0	0/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1		
Fatty alcohol sulfonates	—	—	aqueous	(Xn, Xi)	1/1	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	1/1	0/0	3/4	1/0	1/0	0/0	detergents	
Ferric chloride	FeCl ₃	007705-08-0	saturated	Xn	1/1	1/1	3/0	1/0	0/0	1/0	4/4	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Ferric nitrate	Fe(NO ₃) ₃	010421-48-4	aqueous	(O, Xn)	1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Ferric nitrate	Fe(NO ₃) ₃	010421-48-4	saturated	O, Xn	1/1	1/1	1/0	1/0	0/0	1/0	(3)	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/0	0/0	4/4	1/1	1/1	1/1		
Ferric sulfate	Fe ₂ (SO ₄) ₃	010028-22-5	saturated	Xi	1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	0/0	4/4	1/1	1/1	1/1		
Ferrous chloride	FeCl ₂	007758-94-3	saturated	Xn	1/1	1/1	3/0	1/0	(2)	1/0	(3)	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	(1)	0/0	4/4	(2)	1/1	1/1		
Ferrous sulfate	FeSO ₄	007720-78-7	saturated	(Xn)	1/1	1/1	(2)	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	0/0	4/4	1/1	1/1	1/1			
Ferrous sulfate	FeSO ₄	007720-78-7	aqueous	(Xn)	1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1		
Ferrous sulfate	FeSO ₄	007720-78-7	—	Xn	1/1	1/1	(2)	1/0	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	0/0	4/4	1/1	1/1		
Fire-damp	—	—	—	F+	X	0/0	0/0	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	mainly methane		
Fixer for fotos	—	—	—	?	1/0	1/1	1/0	(2)	0/0	0/0	1/0	1/1	0/0	0/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/0	1/0			
Fluid 101, 100°C	—	—	—	?	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	3	0	0	0	0	Brake fluid, based on polyglycoles	
Fluorides	—	—	—	T	1/1	1/1	(2)	1/1	(2)	1/1	(1)	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	(1)	0/0	0/0	K	K			
Fluorine	F ₂	007782-41-4	—	O, T+, C+	4/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	1/1	4/4	4/4	3/0	4/4	0/0	4/4	(4)	(4)	0/0	
Fluorobenzene	C ₆ H ₅ F	000462-06-6	—	F, (Xn)	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0			
Fluorocarbons	—	—	—	?	0/0	0/4	(2)	(3)	(2)	0/0	(2)	(3)	4/4	0/0	0/0	0/0	0/4	1/1	0/0	1/1	(3)	(3)	(3)	(3)	0/0	(1)	0/0	0/0	resistance depends on type		
Formaldehyde solution	CH ₂ O	000050-00-0	10 %	Xn	1/1	1/1	3/3	1/2	1/0	1/2	1/2	1/1	3/4	2/3	2/3	3/3	1/3	1/1	1/1	1/1	1/1	1/0	3/0	(2)	0/0	1/1	1/1	1/1	1/1		
Formaldehyde solution	CH ₂ O	000050-00-0	30 %	T	1/1	1/1	3/3	1/2	1/0	0/0	1/2	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	1/1	1/1		
Formaldehyde solution	CH ₂ O	000050-00-0	40 %	T	1/2	2/3	1/3	1/2	1/0	1/2	1/2	1/2	4/4	2/3	2/3	3/3	0/4	1/1	1/1	1/1	1/1	1/0	3/0	(3)	0/0	1/1	1/1	1/1	1/1		
Formamide	CH ₃ NO	000075-12-7	techn. pure	T/Xi	1/1	1/1	1/0	(3)	0/0	0/0	1/0	1/1	1/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(3)	3/0	273	4/4	0/0	1/1	1/1	1/1	1/1		
Formic acid	CH ₂ O ₂	000064-18-6	—	1 C, F	X	1/1	1/2	4/4	3/3	0/0	1/2	4/4	1/2	3/3	2/2	2/3	0/0	1/3	1/1	1/1	1/1	1/1	3/4	4/4	4/4	0/0	(3)	1/3	1/2	1/1	Hydrogen carboxylic acid; Methanoic acid; Amino acid; Formylic acid
Formic acid	CH ₂ O ₂	000064-18-6	98-100 %	C, F+, T	X	1/1	1/2	4/4	3/4	0/0	1/3	4/4	1/3	3/4	3/4	1/3	3/4	1/1	(1)	1/1	1/1	3/4	4/4	4/4	0/0	1/0	1/3	1/2	1/0		
Formic acid	CH ₂ O ₂	000064-18-6	3 %	Xi	1/1	1/2	3/4	1/2	1/0	1/2	2/4	1/2	1/2	2/2	2/3	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(3)	4/4	0/0	(3)	1/2	1/1	1/1		
Freon 11	-> see: Trichlorofluoromethane																														
Freon 11	-> see: Trichlorofluoromethane																														
Freon 112	-> see: Tetrachlorodifluoroethane																														
Freon 112	-> see: Tetrachlorodifluoroethane																														
Freon 113	-> see: Trichlorotrifluoroethane																														
Freon 113	-> see: Trichlorotrifluoroethane																														
Freon 114	-> see: Dichlorotetrafluoroethane																														
Freon 114	-> see: Dichlorotetrafluoroethane																														
Freon 114 B2	-> see: Dibromotetrafluoroethane																														
Freon 114 B2	-> see: Dibromotetrafluoroethane																														
Freon 115	-> see: Chloropentafluoroethane																														
Freon 115	-> see: Chloropentafluoroethane																														
Freon 12	-> see: Dichlorodifluoromethane																														
Freon 12	-> see: Dichlorodifluoromethane																														
Freon 13	-> see: Chlorotrifluoromethane																														
Freon 13	-> see: Chlorotrifluoromethane																														
Freon 13 B1	-> see: Bromotrifluoromethane																														
Freon 13 B1	-> see: Bromotrifluoromethane																														
Freon 14	-> see: Carbon tetrafluoride																														
Freon 14	-> see: Carbon tetrafluoride																														
Freon 142b	-> see: Chlorodifluoroethane																														
Freon 142b	-> see: Chlorodifluoroethane																														

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics													fluoroplastics		elastomers		metals		Hazard by C	COMMENT							
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FKM / FKM			NBR	SI	AL	V2A	V4A		
Isobutanol	C ₄ H ₁₀ O	000078-83-1		Xn	X	1/1	1/1	(2)	1/2	(2)	1/2	1/0	1/1	2/2	1/2	1/2	1/2	0/0	3/4	1/1	(1)	1/1	(1)	1/1	1/0	1/0	3/4	0/0	1/0	(1)	(1)	0/0	Methyl-1-propanol, 2-; Isopropyl carbinol; Isobutyl alcohol
Isobutyl acetate	C ₈ H ₁₆ O ₂	000110-19-0		F	X	0/0	0/0	(2)	(4)	0/0	(4)	1/0	(3)	4/4	0/0	3/0	4/4	0/0	0/0	0/0	(1)	1/0	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)	0	Methylpropyl acetate, 2-; Methylpropyl ethanoate, Beta-	
Isobutyl alcohol						-> see: Isobutanol																											
Isobutyltrimethylmethane						-> see: Trimethylpentane, 2,2,4-																											
ISO-Fluid			liquid	Xn, N	X	0/0	2/3	(1)	(3)	1/0	(4)	1/0	3/4	4/4	0/0	1/3	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	1/0	0/0	1/1	1/1	1/1	0/0			
ISO-Fluid A				(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	1/0	0/0	(1)	(1)	(1)	(1)			
ISO-Fluid B				(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)	(1)					
ISO-Fluid C				(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)	(1)				
ISO-Fluid D				(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	4/4	0/0	(1)	(1)	(1)	(1)				
Iso-octane						-> see: Trimethylpentane, 2,2,4-																											
Isopropyl acetate	C ₇ H ₁₄ O ₂	000108-21-4		F, Xi	X	1/2	2/3	1/0	4/4	(3)	2/3	1/0	2/3	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/1	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0			
Isopropyl alcohol	C ₃ H ₈ O	000067-63-0	techn. pure	F, Xi	X	1/1	1/1	1/0	1/2	1/0	1/2	1/0	1/1	2/2	1/2	1/2	1/2	1/4	1/4	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	(2)	(1)	(1)	0/0		
Isopropyl carbinol						-> see: Isobutanol																											
Isopropyl chloride	C ₃ H ₇ Cl	000075-29-6		F, Xn	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0					
Jam						1/1	1/1	(1)	1/1	1/1	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(2)	1/1	1/1	1/1			
Juices						1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(2)	1/1	1/1	1/1			
Kapsolat						-> see: Ethylene glycol monomethyl ether oleate																											
Kerosene		008008-20-6		(Xn)	X	2/2	3/4	(1)	4/4	1/1	2/3	1/1	3/3	4/4	2/3	1/1	0/0	0/0	2/3	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0		lamp oil	
Kerosene			techn. pure	Xn, N	X	1/3	3/4	1/0	3/0	(1)	0/0	1/1	1/3	4/4	1/0	1/0	3/0	3/4	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	1/1	1/1	1/1			
Lactames				?		0/0	0/0	0/0	0/0	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	4/4	4/4	0/0	(2)	(1)	(1)			cyclic amides		
Lactic acid	C ₃ H ₆ O ₃	000050-21-5	3 %	?		1/1	1/2	(3)	1/2	1/0	1/2	2/4	1/2	2/2	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/4	1/1	(2)	0/0	(1)	1/1	1/1	1/1	1/1			
Lactic acid	C ₃ H ₆ O ₃	000050-21-5	80 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/1	1/1	1/1	2/3	2/3	1/1	1/2	1/1	1/1	1/3	3/4	1/1	1/4	0/0	1/0	1/3	1/2	1/1			
Lactic acid	C ₃ H ₆ O ₃	000050-21-5	85 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/2	2/2	1/1	2/3	2/3	1/1	1/2	1/1	1/1	1/3	3/4	1/1	1/4	0/0	1/0	1/3	1/2	1/1			
Lactose	C ₁₂ H ₂₂ O ₁₁	000063-42-3	aqueous			1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0		
Lanolin		008006-54-0	techn. pure			3/3	3/3	1/0	1/0	1/0	0/0	(2)	3/3	1/1	0/0	3/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	1/1			
Lard						0/0	0/0	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	2/0	1/0	1/0	0/0	(1)	1/1	1/1	1/1				
Latex				?		0/0	0/0	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(3)	(1)	(2)	0/0	(2)	(1)	(1)	1/1		1/1	dispersion of rubber	
Laurel			ground	?		0/0	0/0	(2)	(2)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)	(1)					
Lauryl alcohol	C ₁₂ H ₂₅ O	000112-53-8	100 %	Xi		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	(1)	(1)	0/0			
Lauryl chloride	C ₁₂ H ₂₅ Cl	000112-52-7	100 %	(Xi)		0/0	0/0	(2)	(3)	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(1)	(3)	0/0	(3)	0/0	0/0					
Lavender oil		008000-28-0		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	(1)	(1)	(1)				
Lead acetate	C ₂ H ₃ PbO ₄	000301-04-2	aqueous	T, N		1/1	1/1	3/0	1/0	(2)	1/0	1/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	3/0	0/0	4/4	1/1	1/1	1/1			
Lead acetate	C ₂ H ₃ PbO ₄	000301-04-2		T, N		1/1	1/1	3/0	1/0	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	2/2	0/0	4/4	1/1	1/1	1/1			
Lead nitrate	Pb(NO ₃) ₂	010099-74-8	aqueous	O, T, N		1/1	1/1	(3)	(2)	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1			
Lead nitrate	Pb(NO ₃) ₂	010099-74-8		O, T, N		1/1	1/1	(3)	(2)	0/0	(2)	1/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1			
Lead stearate	C ₃₆ H ₇₁ PbO ₄	001072-35-1		?		1/1	1/1	(2)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)			small solubility - no chemical effect expected	
Lead sulfate	PbSO ₄	007446-14-2		(T, N)		1/1	1/1	(2)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	(1)	(1)	(1)	(1)	0/0			small solubility - no chemical effect expected	
Lead tetraethyl (TEL)	C ₈ H ₁₈ Pb	000078-00-2	techn. pure	T+	X	1/0	1/0	1/4	3/0	(2)	(4)	(2)	2/4	0/0	0/0	1/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/0	0/0	(2)	(1)	(1)	1/1				
Lemon juice						1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	1/0	1/1	0/0	(1)	1/1	1/1				
Lemon oil		084929-31-7		Xi	(X)	0/0	0/0	(2)	(3)	1/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	3/3	0/0	1/0	(1)	(2)	4/4	(2)	3/3	0/0	1/1	(1)	(1)			mainly limonene	
Lemongrass oil		008007-02-1		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	(4)	0/0	(1)	(1)	(1)				
Ligroin		008032-32-4		F, Xn	X	0/0	0/0	(2)	1/0	(2)	(4)	(2)	(3)	3/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	1/1			petroleum ether
Lime chloride	[3 x CaCl(OCl) + Ca		aqueous	?		0/0	0/0	4/4	(2)	3/0	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1			chloride of lime, bleach	
Lime chloride	[3 x CaCl(OCl) + Ca			O, C		0/0	0/0	4/4	(2)	3/0	0/0	4/4	1/1	1/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1			chloride of lime, bleach
Limonene, DL-	C ₁₀ H ₁₆	000138-86-3		Xn	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1				
Linseed oil		008001-26-1	techn. pure			1/1	1/3	1/0	1/0	1/0	1/1	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1				

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics											fluoroplastics		elastomers		metals		Hastelloy C	COMMENT									
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE			PVDF	EPDM	FKM / FKM	NBR	SI	AL	V2A	V4A	
Mustard	—	—	—	—	0/0	0/0	(2)	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	1/1	(1)	(1)	(2)	1/0	1/0	0/0	(2)	1/0L	1/0L	1/0L	0/0				
Naphtha	—	008032-32-4	—	(Xn)	1/3	3/4	1/0	(2)	(1)	1/0	1/0	1/3	3/0	1/0	1/0	4/4	0/0	0/0	(1)	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	petroleum ether		
Naphthalene	C ₁₀ H ₈	000091-20-3	100 %	F, Xn	X	0/0	1/3	1/0	(3)	0/0	0/0	1/2	1/3	3/4	1/0	4/4	4/4	1/4	0/0	(1)	1/1	1/3	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0		
Naphthalene (in alcohol)	—	—	—	F, Xn	X	1/4	1/4	(2)	(3)	0/0	0/0	1/2	1/3	3/4	0/0	0/0	0/0	3/4	0/0	(1)	1/1	(2)	4/4	(3)	(3)	0/0	(1)	(1)	(1)	0/0		
Neon	Ne	007440-01-9	—	—	—	0/0	0/0	1/0	(1)	1/1	0/0	1/1	(1)	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1	0/0		
Nickel acetate	C ₄ H ₈ NO ₄	000373-02-4	aqueous	(T, N)	—	1/1	1/1	(3)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/0	0/0	4/4	0/0	0/0	0/0	0/0		
Nickel dichloride	NiCl ₂	007718-54-9	saturated	T	—	1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1		
Nickel dichloride	NiCl ₂	007718-54-9	aqueous	T	—	1/1	1/1	(3)	(2)	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1		
Nickel sulfate	NiSO ₄	007786-81-4	saturated	Xn	—	1/1	1/1	1/0	1/0	(1)	1/0	2/0	1/1	1/1	0/0	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1		
Nickel sulfate	NiSO ₄	007786-81-4	aqueous	Xn	—	1/1	1/1	(3)	1/0	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1	1/1		
Nickelous nitrate	Ni(NO ₂) ₂	013138-45-9	saturated	(O, Xn)	—	1/1	1/1	(3)	(2)	(1)	1/0	(2)	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1		
Nicotine	C ₁₀ H ₁₄ N ₂	000054-11-5	—	T+	—	1/0	1/0	(3)	(3)	0/0	(2)	1/0	1/0	1/0	1/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/1	0/0	(1)	(1)	(1)	(1)	0/0	0/0		
Nicotinic acid	C ₆ H ₇ NO ₂	000059-67-6	diluted	Xi	—	1/1	1/1	(3)	(2)	0/0	(3)	1/0	0/0	1/1	0/0	0/0	0/0	1/1	(1)	(1)	(2)	(3)	(2)	0/0	(3)	0/0	0/0	0/0	0/0	0/0		
Nitric acid	HNO ₃	007697-37-2	1-10 %	C	—	1/1	1/1	4/4	1/2	(2)	1/1	4/4	1/1	2/4	1/3	1/2	0/0	1/3	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	3/4	1/1	1/1	1/1		
Nitric acid	HNO ₃	007697-37-2	50 %	C+	—	2/4	3/4	4/4	4/4	(2)	2/4	4/4	3/4	4/4	2/3	2/3	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2		
Nitric acid	HNO ₃	007697-37-2	66 %	C+	—	2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2	1/2		
Nitric acid	HNO ₃	007697-37-2	100 %	O, C+	—	4/4	4/4	4/4	4/4	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	4/4	0/0	1/1	1/1	4/4	4/4	4/4	4/4	0/0	1/1	2/3	3/3	?		
Nitric acid	HNO ₃	007697-37-2	70 %	O, C+	—	2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	4/4	1/2	1/2	1/2	1/2		
Nitric acid	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Nitric acid, ammonium nitrate	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Nitric acid, magnesium salt	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Nitric acid, potassium salt	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Nitro benzoic acid	C ₇ H ₅ NO ₄	—	—	(Xn)	—	1/0	1/0	(3)	(3)	0/0	0/0	(3)	1/0	0/0	0/0	1/0	0/0	0/0	(1)	(1)	(2)	3/0	(3)	(2)	0/0	(3)	0/0	0/0	0/0	0/0	0/0	isomer not indicated in the source
Nitro reducer	—	—	—	?	X	0/0	0/0	3/0	(4)	0/0	(4)	(3)	(3)	4/4	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)	(1)	0/0	0/0	solvent cleaner mixture
Nitrobenzene	C ₆ H ₅ NO ₂	000098-95-3	—	T	—	3/4	4/4	4/4	4/4	1/0	4/4	3/0	2/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	1/1	0/0	
Nitroethane	C ₂ H ₅ NO ₂	000079-24-3	—	Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	(1)	0/0	0/0	
Nitrogen	N ₂	007727-37-9	—	—	—	0/0	0/0	1/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	
Nitrogen hydride	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Nitrogen tetroxide	N ₂ O ₄	010544-72-6	—	(O), T+, C	—	0/0	0/0	3/0	(3)	1/0	0/0	4/4	1/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	4/4	4/4	0/0	(2)	(1)	(1)	(1)	0/0	0/0	0/0	
Nitroglycerine	C ₃ H ₅ (NO ₃) ₃	000055-63-0	diluted	(E, T+)	—	0/0	0/0	(3)	(3)	0/0	(2)	(2)	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/0	(3)	1/0	1/0	4/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	
Nitrohydrochloric acid	C ₂ H ₅ NO ₂ + HCl	008007-56-5	—	C	—	4/4	4/4	4/4	4/4	3/3	4/4	4/4	4/4	4/4	4/4	3/4	1/1	(2)	1/1	3/0	4/4	4/4	4/4	0/0	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4
Nitropropane	C ₃ H ₇ NO ₂	—	—	(T)	—	0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	(1)	0/0	0/0	
Nitrose gases	—	—	diluted	T	—	1/1	0/0	3/0	4/4	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	3/0	4/4	0/0	(2)	(1)	(1)	0/0	0/0	nitrogen monoxide + nitrogen dioxide	
Nitrotoluene	C ₇ H ₇ NO ₂	001321-12-6	—	techn. pure	T	1/3	1/3	4/4	4/4	1/0	(4)	3/0	1/3	4/4	0/0	4/4	4/4	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	1/1	0/0	
Nitrous acid, sodium salt	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Nitrous oxide	N ₂ O	010024-97-2	—	(O)	—	0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	2/0	1/0	1/0	0/0	1/1	(1)	(1)	0/0	0/0	nitric oxide	
Nonanol	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Nonyl alcohol	C ₉ H ₂₀ O	000143-08-8	100 %	Xn, Xi	—	0/0	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)	0/0	0/0	Nonanol; Pelargonic alcohol; Octyl carbinol
Nutmeg oil	—	008008-45-5	—	(Xn)	—	0/0	0/0	(2)	4/4	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/4	0/0	(1)	(1)	(2)	(4)	(3)	(3)	0/0	(1)	(1)	(1)	0/0	0/0	
Octafluoropropane	C ₃ F ₈	000076-19-7	—	?	—	0/0	0/0	1/0	(3)	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/0	1/0	1/0	0/0	(3)	0/0	0/0	0/0	0/0	0/0	
Octane	C ₈ H ₁₈	000111-65-9	—	F, Xn	X	1/1	1/1	1/0	2/3	(1)	1/1	1/0	1/1	4/4	2/3	3/4	3/3	1/1	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1	1/1	0/0	0/0	
Octyl carbinol	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Octyl cresol ?	C ₁₅ H ₂₄ O	—	100 %	?	—	3/0	3/0	(3)																								

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics													fluoroplastics		elastomers		metals		Hastelloy C	COMMENT																										
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM			FPM / FKM	NBR	SI	AL	V2A	V4A																				
Trichloroethylene (TRI)	C ₂ HCl ₃	000079-01-6	100 %	Xn	3/4	4/4	3/0	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/0	1/1	4/4	1/3	4/4	0/0	1/3	(1/1L) ¹⁾	(1/1L) ¹⁾	1/0	¹⁾ Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.																
Trichlorofluoromethane	CCl ₃ F	000075-69-4		N	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(3)	(1)	0/0	4/4	2/0	1/0	0/0	(3)	0/0	0/0	0/0																		
Trichlorophenol	C ₆ H ₂ Cl ₃ O	—		(Xn, Xi)	0/0	0/0	(3)	(4)	0/0	0/0	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(4)	(3)	(4)	0/0	(3)	0/0	(3)	0/0	(3)	0/0	0/0	0/0	0/0	isomer not indicated in the source																	
Trichlorotrifluoroethane	C ₂ Cl ₃ F ₃	000076-13-1		?	0/0	0/0	1/0	(3)	1/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0	0/0	0/0																		
Trichlorotrifluoroethane	C ₂ Cl ₃ F ₃	—	100 %	?	4/4	3/4	1/0	3/0	0/0	0/0	1/0	4/4	4/4	1/0	3/4	4/4	3/3	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0	(3)	0/0	0/0	0/0	0/0	0/0	isomer not indicated in the source																	
Tricresyl phosphate (TCF)	C ₂₁ H ₂₁ PO ₄	—	techn. pure	T/Xn, N	1/1	1/1	1/0	4/4	1/0	0/0	1/0	1/3	4/4	4/4	4/4	4/4	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	1/1	1/0	1/0	2/0	4/4	4/4	0/0	(1)	1/1	1/1	isomer not indicated in the source																
Triethanolamine (TEA)	C ₆ H ₁₅ NO ₃	000102-71-6	techn. pure	Xi	1/1	1/2	(2)	(2)	1/0	0/0	2/2	1/1	1/1	0/0	3/0	4/4	1/1	0/0	1/1	1/0	1/0	2/0	4/4	4/4	0/0	(1)	(1)	(1)	(1)	(1)	0/0	0/0																			
Triethylamine (TEA)	C ₆ H ₁₅ N	000121-44-8	techn. pure	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	1/1	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	3/4	4/4	3/0	3/4	0/0	(1)	(1)	(1)	(1)	(1)	0/0	0/0																			
Triethylene glycol	C ₆ H ₁₄ O ₄	000112-27-6		Xi	1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	(3)	0/0	(1)	(1)	(1)	(1)	(1)	0/0	0/0																			
Triethylene glycol diacetate	C ₁₀ H ₁₈ O ₆	000111-21-7		?	0/0	0/0	(3)	(3)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)	(1)																						
Trihydroxypropane, 1,2,3-	-> see: Glycerol																																																		
Triiodomethane	-> see: Iodoform																																																		
Triisopropylbenzene	C ₁₅ H ₂₄	000717-74-8		—	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	1/0	0/0	1/1	(1)	(1)																							
Trimethylbenzene, 1,2,4-	C ₉ H ₁₂	000095-63-6		Xn	X	0/0	0/0	(1)	(4)	0/0	0/0	(2)	3/3	4/4	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(2)	4/4	0/0	1/1	1/1	1/1	1/1	1/1	0/0	0/0																			
Trimethylolpropane	C ₈ H ₁₄ O ₃	000077-99-6	aqueous	—	0/0	0/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	4/4	0/0	(1)	(1)	(1)																						
Trimethylpentane, 2,2,4-	C ₈ H ₁₈	000540-84-1	techn. pure	F, Xn	X	1/3	1/3	1/0	(2)	1/0	(4)	1/0	1/3	3/4	1/0	1/0	4/4	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	Iso-octane; Isobutyltrimethylmethane																
Triocetyl phosphate	C ₂₄ H ₅₀ PO ₄	000078-42-2	techn. pure	(Xn)	3/0	1/0	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	(1)	(1)	(1)	(1)	0/0	0/0	0/0	0/0	Tris(2-ethylhexyl) phosphate																	
Tripolyethylene glycol (TPG)	C ₈ H ₂₀ O ₄	024800-44-0		(—)	1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/1	1/1	2/3	0/0	0/0	0/0	1/1	1/1	(2)	(3)	(2)	(3)	0/0	(1)	(1)	(1)																							
Trisodium phosphate	Na ₃ PO ₄	007601-54-9		Xi	1/1	1/1	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	1/1	0/0	(4)	1/1	1/1																						
Turbine oil (based on mineral oil)	—	—		?	0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	(2)	1/0	0/0	1/1	1/1	1/1																							
Turpentine surrogate	—	—		Xn, N	X	0/0	0/0	1/0	(3)	1/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	3/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1																	
Two-stroke oil	—	—	100 %	—	0/0	1/3	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1																	
Undecanol	C ₁₁ H ₂₄ O	000112-42-5		Xi	1/2	1/3	(1)	2/3	(1)	1/2	1/0	1/2	2/2	3/3	1/3	0/0	1/1	1/2	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(1)	(1)	(1)																							
Urea	CH ₄ N ₂ O	000057-13-6	aqueous	Xi	1/1	1/1	1/0	1/1	0/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	0/0	1/1	1/0	1/0	1/0	1/0	1/0	1/1	1/1																	
Urea	CH ₄ N ₂ O	000057-13-6		Xi	1/1	1/1	1/0	1/1	1/0	1/2	1/1	1/1	1/2	3/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/1	1/0	1/0	1/0	1/0	1/0	1/1																	
Uric acid	C ₅ H ₄ N ₄ O ₃	000069-93-2		Xi	1/1	1/1	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	4/4	1/1	1/1	1/0	1/0	0/0	0/0	0/0	0/0																	
Urine	—	—		—	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	3/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1																	
Urotropin	-> see: Hexamethylenetetramine																																																		
Valerian drops	—	—		?	0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/0	0/0	1/1	1/1	(1)	(3)	(3)	(2)	0/0	(2)	(1)	(1)																							
Vaseline	—	008009-03-8	techn. pure	(—)	3/4	2/3	1/0	1/0	1/0	0/0	—	1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	petrolatum																
Vaseline oil	—	008012-95-1	100 %	?	0/0	1/3	1/0	(2)	1/0	1/0	—	1/3	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	paraffin oil																
Vaseline oil	—	008012-95-1		?	1/1	1/3	1/0	1/0	0/0	1/1	1/3	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	paraffin oil																
Vegetable oils	—	—		—	0/0	0/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1	1/1																							
Vinegar	C ₂ H ₄ O ₂	000064-19-7		(Xi)	1/1	1/3	4/4	1/2	1/1	1/0	1/3	1/1	1/0	1/0	1/0	3/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/2	1/1	1/1	1/1	1/1	1/1	1/1																	
Vinyl acetate	C ₄ H ₆ O ₂	000108-05-4	techn. pure	F	X	0/0	1/1	1/0	4/4	(3)	(4)	1/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	1/0	3/0	3/3	0/0	(1)	(1)	(1)	(1)	0/0	0/0	0/0	0/0																		
Vinyl carbinol	-> see: Allyl alcohol																																																		
Vinyl chloride (VCM)	C ₂ H ₂ Cl	000075-01-4	techn. pure	F+, T	X	0/0	0/0	1/1	(4)	1/1	0/0	(3)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	1/1	3/0	3/0	4/4	0/0	(1)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	Chloroethene; Chloroethylene																	
Vinyl cyanide	-> see: Acrylonitrile																																																		
Vinylidene chloride	C ₂ H ₂ Cl ₂	000075-35-4		F+, Xn	X	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	2/3	1/1	(1)	(2)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0																
Vitamin C	C ₆ H ₈ O _{6</}																																																		

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics													fluoroplastics		elastomers		metals		Hastelloy C	COMMENT							
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM			FPN / FKM	NBR	SI	AL	V2A	V4A	
Zinc oxide ointment	—	—	—	~	0/0	0/0	(1)	(2)	(2)	0/0	(2)	(2)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	(1)	1/1	(1)	(1)	0/0	
Zinc phosphate	Zn ₃ (PO ₄) ₂	007779-90-0	saturated	?	1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	(2)	(1)	(1)	0/0		
Zinc sludge	—	—	—	?	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	(3)	0/0	0/0	0/0		
Zinc stearate	C ₃₆ H ₇₀ ZnO ₄	000557-05-1	—	Xi	1/1	1/1	(1)	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	1/1	(2)	0/0	(2)	(1)	(1)		
Zinc sulfate	ZnSO ₄	007733-02-0	10 %	—	1/1	1/1	(3)	1/0	(2)	1/0	2/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	1/1	
Zinkchlorid	ZnCl ₂	007646-85-7	10 %	C, Xn	1/1	1/1	3/4	1/0	0/0	1/1	2/0	1/1	1/3	0/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/4L	1/3L	1/1	

Chemical resistance

Two values are given per substance
left number = value at +20°C / right number = value at +50°C.

0	no data available
1	resistant
2	practically resistant
3	partially resistant
4	not resistant
K	no general information available
L	danger of pitting or stress-cracking corrosion
()	estimated value

Hazard notes

E	explosive
O	oxidizing
F	highly flammable
F+	extremely flammable
T	toxic
T+	very toxic
C	corrosive
Xn	harmful
Xi	irritant
N	dangerous for the environment

Description of the materials

Thermoplastics

HDPE	Polyethylene (high density)
LDPE	Polyethylene (low density)
PA	Polyamide (Nylon)
PC	Polycarbonate
PETG	Polyethylene terephthalate glycol (PET copolymer)
PMP	Polymethylpentene (TPX)
POM	Polyoxymethylene, polyacetal
PP	Polypropylene
PS	Polystyrene
PSU	Polysulfone
PVC	Polyvinyl chloride
SAN	Styrene-acrylonitrile

Fluoroplastics

E-CTFE	Ethylene-chlorotrifluoroethylene (Halar)
ETFE	Ethylene-tetrafluoroethylene
FEP	Tetrafluoroethylene-perfluoropropylene (Teflon, FEP)
PTFE	Polytetrafluoroethylene (Teflon)
PVDF	Polyvinylidene fluoride

Elastomers

EPDM	Ethylene-propylene-diene rubber
FPM/FKM	Fluorinated rubber (Viton)
NBR	Acryl-nitrile-butadiene rubber
SI	Silicone rubber

Metals

Al	Aluminium
V2A	Stainless steel 1.4301 (AISI 304)
V4A	Stainless steel 1.4401 (AISI 316)
Hastelloy C	Nickel-chromium-molybdenum alloy